

# **GENERAL DYNAMICS**

## Bath Iron Works

---

### **NSRP Cleanable Non-Skid Deck Covering Project**



**BIW Process Control  
FY2023/24**

# BIW-Panel Project Scope of Work

## Initial Outline

---

**Determine if polysiloxane non-skid can easily and effectively be cleaned and kept clean throughout the new construction process eliminating premature failure and costly rework.**

- ✓ Five 12'x16' test areas. Contaminated with grit and industrial debris.
- ✓ Testing effectiveness of different methods of cleaning and care & protection.
- ✓ Visually compare level of cleanliness between different manufactures and types of non-skid polysiloxane vs legacy non-skid.
- ✓ Determine best practices for cleaning and care & protection methods of non-skids.

# Initial Primer & Non-Skid Plan

## Non-Skid Products

Vendor A= ITW MS7CZ and MS375

Vendor B= NCP SiloxoPrime and SiloxoGrip

Vendor C= Randolph Randogrip Metal Primer and Siloxoskid

C2R= Rolled

C2S= Sprayed

## Care & Protection Methods



Green Rubber



Breather Shield



Rhino Tile over Breather Shield




Intergard 5400 Peelable coating



Rust Runner

# Initial Test Platform Scope

## Dry Dock Deck



# Proposed Testing Materials

Manufacture	Product Description	Kit Size
NCP Coatings	<u>SiloxoPrime</u> Primer (quote)	5 gl kit
	<u>SiloxoGrip</u> Non-Skid (quote)	5 gl kit
	Estimated Freight (quote)	NA
Randolph (SW)	<u>Randogrip</u> Metal Primer (quote)	5 gl kit
	<u>Randogrip</u> Siloxoskid (quote)	5 gl kit
American Safety	MS7CZ Epoxy Primer (contract)	5 gl kit
	MS-375G Non-Skid (contract)	5 gl kit
Entry Point Int.	Rhino Tile FR – 500 pieces per pallet (quote)	Pallet
	Ramped Edges – 50 per box (quote)	Box
	<u>BreatherShield</u> (quote)	Roll
United Rental	1 week rental HW Pressure Washer (quote)	1 week
	1 week rental Dry Ice Removal (quote)	1 week
BIW <u>Miscelanous</u>	In House Use Items:	

# BIW – Panel Project SOW

## DELIVERABLE SCHEDULE

Deliverable	Team Member(s)	Due Date
Develop Project Plan, Schedule of Events and Test Platforms.	BIW – Brian Thiele BIW – David Kinee	03/30/23 Complete
Develop Inspection Criteria.	BIW – Brian Thiele BIW – David Kinee	07/20/23 Complete
Install Samples to Project Plan (surface prep, prime & nonskid).	BIW – Brian Thiele BIW – David Kinee	08/7/23-9/01/23 Complete
Project Status Update – Q1.	BIW – Brian Thiele BIW – David Kinee	09/20/23 Complete
Monthly Weathering and Visual Inspection Checks.	BIW – Brian Thiele BIW – David Kinee	9/01/23-5/01/24 Complete
Project Status Update – Q2.	BIW – Brian Thiele BIW – David Kinee	12/20/23 Complete
Initial Cleaning Testing, Evaluation and Re-Care & Protect.	BIW – Brian Thiele BIW – David Kinee	11/15/23 C&P has not been reinstalled. The methods used did not withstand the weather conditions. We removed loose items and left those that remained intact. Most of the Intergard 5400 remains intact
Final Cleaning Testing and Care & Protection Evaluation.	BIW – Brian Thiele BIW – David Kinee	05/07/24 – 05/09/24 Complete
Project Status Update – Q3.	BIW – Brian Thiele BIW – David Kinee	03/20/24 Complete
Final Report with Recommendations – Q4.	BIW – Brian Thiele BIW – David Kinee	06/20/2024

## TECHNOLOGY TRANSFER / IMPLEMENTATION APPROACH



# Cleaning Test Method Ranking Criteria

## No Care & Protection Sample Set

### No Care & Protection Sample Set:

- **Contamination method-**
  - ✓ All sample sets will be contaminated with blast fines from recycled 30/60HG steel grit and 390 steel shot to simulate industrial debris and left-over steel shot often found after deck blasting
  - ✓ Contamination area will be approximately a 3' wide across the entire length of each sample set
- **Cleaning method-** (cleaning methods will be equidistant on each sample set)
  - ✓ SpongeBlast with plastic
  - ✓ Hot water pressure wash with Iron Out
  - ✓ Dry ice
- **Ranking / Rating will follow a 0 (zero) to 5 rating with 0 being unacceptable to 5 being the best**
  - ✓ **5** = With air blow down only no staining remains
  - ✓ **4** = With proposed cleaning methods no staining
  - ✓ **3** = With proposed cleaning methods 1-10% staining remains
  - ✓ **2** = With proposed cleaning method 11-25% staining remains
  - ✓ **1** = With proposed cleaning method 26-50% staining remains
  - ✓ **0** = With proposed cleaning method greater than 50% staining remains.

# Cleaning Test Method Ranking Criteria

## Care & Protection Sample Set

### Care & Protection Sample Set:

- Care & Protection Method-

- ✓ Care & Protection will be applied over at least 90% of each sample set
- ✓ 50% of that will be covered with green rubber and 50% will be covered with Entry Point BreatherShield and Rhino Tile FR

- Containment

- ✓ All
- st
- ✓ Co

- Cleaning

- ✓ Sp
- ✓ H
- ✓ D

- Ranking

- ✓ 5
- ✓ 4
- ✓ 3
- ✓ 2
- ✓ 1
- ✓ 0

# Not Tested




and 390  
blasting  
sample set

best



# Start Of Deck Blasting Surface Prep

460 steel shot a blast media



# Final Deck Blasting Surface Prep




# 2 Coats Of Primer Prior To Non-Skid

## Some With Proprietary And Some with 23236





# Masking And Start Of Non-Skid



# Dry Dock Wing Wall View Of Completed Non-Skid





# Updated Primer & Non-Skid Plan

## **No Care & Protection Sample Set:** (all sqft listed are approximate)

### □ **Vendors-**

- ✓ Vendor A = American Safety (MS7CZ Primer & MS375G), 12' x 12' – rolled
- ✓ Vendor B = NCP Coatings (SiloxoPrime & SiloxoGrip), 12' x 12' – rolled
- ✓ Vendor C = Randolph (Randogrip Primer & Randogrip Siloxoskid) 12' x 12' – rolled
- ✓ Vendor C1-S = Randolph (SeaGuard 5000HS Primer & Randogrip Siloxoskid) 12' x 10' – sprayed
- ✓ Vendor C1-R = Randolph (SeaGuard 5000HS Primer & Randogrip Siloxoskid) 12' x 10' – rolled
- ✓ Vendor B1-S = NCP Coatings (SeaGuard 5000HS & SiloxoGrip), 12' x 10' – sprayed


## **Care & Protection Sample Set:** (all sqft listed are approximate)

### □ **Vendors-**

- ✓ Vendor A = American Safety (MS7CZ Primer & MS375G), 12' x 12' – rolled
- ✓ Vendor B = NCP Coatings (SiloxoPrime & SiloxoGrip), 12' x 12' – rolled
- ✓ Vendor C = Randolph (Randogrip Primer & Randogrip Siloxoskid) 12' x 12' – rolled
- ✓ Vendor C1-S = Randolph (SeaGuard 5000HS Primer & Randogrip Siloxoskid) 12' x 10' – sprayed
- ✓ Vendor C1-R = Randolph (SeaGuard 5000HS Primer & Randogrip Siloxoskid) 12' x 10' – rolled
- ✓ Vendor B1-S = NCP Coatings (SeaGuard 5000HS & SiloxoGrip), 12' x 10' – sprayed


# Revised Test Platform

## No Care & Protection



# Revised Test Platform

With Care & Protection





# No Care & Protection Area

IP5400 spray applied on approx. 18in of all sample sets



# Care & Protection Area


Green Rubber ½ & Rhino Tile with Breather Shield ½





# Initial Contamination

40/50 Steel Grit on both C&P and Non-C&P



# Initial Weathered Contamination

40/50 Steel Grit on both C&P and Non-C&P





# Start Of Cleaning Testing 5/7 – 5/9

## Light Sweep Of Heavy Contaminants & Inspection of 5400



# Set Up Of Dry Ice Blasting 2.5 Pellets





# Sample A Dry Ice Before & After





# Sample B Dry Ice Before & After



# Sample C Dry Ice Before & After





# Sample C1-S Dry Ice Before & After




# Sample C1-R Dry Ice Before & After






# Sample B1-S Dry Ice Before & After






# Set Up Of SpongeJet Sponge Blast With Plastic Sponge






# Sample A SpongeJet Before, After & Close Up





# Sample B SpongeJet Before, After & Close Up





# Sample C SpongeJet Before, After & Close Up



# Sample C1-S SpongeJet Before, After & Close Up





# Sample C1-R SpongeJet Before, After & Close Up






# Sample B1-S SpongeJet Before, After & Close Up





# Set Up Of Hot Water Pressure Wash

Approx. 3,500 PSI at 200F– Iron Out Scrubbed In & FSR Rolled In






# Sample A Pressure Wash With Iron Out Before, After & Close Up





# Sample A Pressure Wash With FSR Before, After & Close Up





# Sample B Pressure Wash With Iron Out Before, After & Close Up



# Sample B Pressure Wash With FSR Before, After & Close Up





# Sample C Pressure Wash With Iron Out Before, After & Close Up






# Sample C Pressure Wash With FSR Before, After & Close Up





# Sample C1-S Pressure Wash With Iron Out Before, **After** & Close Up



# Sample C1-S Pressure Wash With FSR Before, After & Close Up





# Sample B1-S Pressure Wash With Iron Out Before, After & Close Up





# Sample B1-S Pressure Wash With FSR Before, After & Close Up





# Near Future

- ❑ **Compiling results from 0-5 ranking parameters.**
- ❑ **Review methods utilized and propose improvements based on results.**
- ❑ **Size of platform would enable some additional testing not associated with current scope of work.**
- ❑ **Work with Elzly on final report out.**

# Q&A